

SURFACE - CEILING - WALL



dustfree



dry



no grease




flat walls
and ceilings



sand and
wash surface

WORKING CONDITIONS



10-35°C
50-95°F



min 40%
max 70%




24hrs

Storage & installation conditions for
Orac Decor products & DecoFix.


Place profiles & adhesives at room
temperature 24 hours before installation.

GLUES


ONLY FULL GUARANTEE WITH DECOFIX




- INTERIOR, POROUS
AND DRY SURFACE




DecoFix PRO
gluing on
wall and ceiling




DecoFix EXTRA
joints




- EXTERIOR
- NON-POROUS AND
HUMID SURFACE
- HUMID PLACES




DecoFix HYDRO
gluing on
wall and ceiling




DecoFix EXTRA
joints




- INTERIOR, POROUS
AND DRY SURFACE




DecoFix PRO
gluing on
wall and ceiling




DecoFix PRO
joints



- NON-POROUS AND
HUMID SURFACE
- HUMID PLACES



DecoFix HYDRO
gluing on
wall and ceiling



DecoFix HYDRO
joints



DecoFix Pro
FDP500 310ml
> 7 to 8m
FDP600 4200ml
> 65 to 110m



DecoFix Extra
FX200 310ml
> min. 80m
FX210 80ml
> min. 20m



DecoFix Hydro
FDP700 290 ml
> 7 to 8 m

- Strong, water-based acrylic glue
- Long-lasting seal between mouldings and the wall and/or ceiling
- For interior applications and porous surfaces (not for humid spaces or outside)
- Remove with damp sponge or cloth
- Should be kept frost free

- Polyurethane-based glue
- Seam joints between the mouldings
- Remove excess glue before hardening (max. 1 hour and repeat after 2-3 hours)
- Clean with acetone or Synth Thinner
- Can be painted after 24 hrs
- The more humidity, the faster the drying time

- Extra strong MS polymer glue
- For exterior applications, damp environments, non-porous surfaces (tiles, glass, ...)
- Remove with soap solution